

# Argent 2.0

12x24 Porcelain



03ARG011224




03ARG151224



03ARG171224



03ARG181224



03ARG201224



03ARG311224



03ARG321224



03ARG331224



03ARG341224



03ARG351224



03ARG361224



03ARG371224



03ARG381224



2x2 Mosaic



4x4 Random Angle Mosaic



Tile: 6x24 - 12x12 - 12x24  
Mosaic: 2x2 - 4x4 Random Angle  
Trim: 4x24 Bullnose - 6x12 Cove Base  
*Not all colors available in all sizes or finishes*

For more information  
and images:



### Technical Characteristics

Test Item	Test Method	Test Result
Breaking Strength	ASTM C648	≥ 450 lbf
Bond Strength	ASTM C482	≥ 200 psi
Chemical Resistance	ASTM C650	Unaffected
Frost Resistance	ASTM C1026	Resistant
Water Absorption	ASTM C373	< 0.50%
Scratch Hardness	Mohs Scale	7
DCOF	AcuTest	0.50-0.60

Nominal Size	Actual Size	Thickness	Finish	Rectified
6" x 24"	5.79" x 23.50"	9.5 mm	Unpolished	Yes
12" x 12"	11.69" x 11.69"	9.5 mm	Unpolished	Yes
12" x 24"	11.69" x 23.50"	9.5 mm	Unpolished	Yes
2" x 2" Mosaic	11.73" x 11.73"	9.5 mm	Unpolished	-
4" x 4" Random Angle	11.73" x 11.73"	9.5 mm	Unpolished	-
4" x 24" Bullnose	3.78" x 23.50"	9.5 mm	Unpolished	-
6" x 12" Cove Base	5.79" x 11.77"	9.5 mm	Unpolished	-

Installation Note: The TCNA recommends rectangular shape tile be installed with maximum of 33% offset in order to resolve any possible lippage from one tile to the next.

